

DUNLOP CHEMTEX 71022 GREEN NYLON/POLYESTER/PVC CHEMICAL-RESISTANT COVERALLS - 791079-12249



The Dunlop Chemtex chemical-resistant coverall is made of nylon/polyester/pvc, is packaged 1 per pack, 1 per case, comes in green and meets ASTM D 6413 standards. Proper sizing is important when buying this product.

SPECIFICATIONS

- Brand: Dunlop
- Trade Name: Chemtex
- Series: 71022
- Material: Nylon / Polyester / PVC
- Color: Green
- Front Closure: Zipper
- Size: S-XL
- Materials Resisted: Ammonium Hydroxide; Butane; Calcium Hypochlorite; Carboic Acid; Citric Acid; Copper Chloride; Copper Sulfate; Diethanolamine; Ferric Chloride; Formaldehyde; Glycerine; Grease; Oil; Phosphoric Acid; Propane; Sodium Hydroxide; Tannic Acid; Triethanolamine; Zinc Acetate
- Special Features: Attached Hood; Elastic Ankles
- Standards Met: ASTM D 6413
- Package Quantity: 1 per pack, 1 per case

Protective Clothing - Degradation Chart

HYDROCARBONS (OILS & SOLVENTS)	CHEMTEx	NEOTEx	PROTEx
ASTM #1 Oil	E	G	G
ASTM #3 Oil	E	F	G
Benzene	G	G	G
Benzyl Chloride	F	F	F
Butane	E	G	G
Carbon Tetrachloride	F	F	F
Castor Oil	G	E	G
Chloroform	G	G	G
Coconut Oil	G	G	G
Cottonseed Oil	G	G	G
Cutting Oil	G	G	G
Cyclohexane	F	G	F
Gasoline (Cracked)	G	G	G
Gasoline (SR)	G	G	G
Grease (All Kinds)	E	E	E
Hexane	G	E	G
Hydraulic Oil	G	E	G
Isooctane	G	E	G
Kerosene (C-T)	G	G	G
Kerosene (PET)	G	G	G
Lard Oil (158 F)	G	G	G
Linseed Oil	G	G	G
Methyl Cellosolve	G	E	G
Methyl Chloride	P	G	P
Methylene Chloride	P	G	P
Mineral Oil	G	G	G
Naphtha	G	F	G
Nitrobenzene	P	G	P
Olive Oil	G	G	G
Perchloroethylene	G	E	G
Petroleum Oil	G	G	G
Petroleum Solvent	G	G	G
Pine Oil	G	G	G
Propane	E	G	E
Toluene (Toluol)	G	E	G
Trichloroethylene	F	G	G
Turpentine	G	G	G
Vegetable Oil	G	G	G
Xylene	G	G	G
Coal Tar Solvent	G	G	G
Beef Tallow (158 F)	G	G	G

KETONES AND ALDEHYDES	CHEMTEx	NEOTEx	PROTEx
Acetone	G	E	G
Acetaldehyde	G	G	G
Benzaldehyde	P	F	P
Butyraldehyde	F	G	G
Chloroacetone	F	G	F
Formaldehyde	E	E	E
Furfural	G	E	G
Methyl Ethyl Ketone	P	G	P
ALCOHOLS			
Amyl Alcohol	G	E	G
Benzyl Alcohol	G	E	G
Butyl Alcohol	P	G	G
Diacetone Alcohol	G	E	G
Diethanolamine	E	E	E
Ethylene Glycol	G	E	E
Ethyl Alcohol	G	E	G
Glycerine	E	E	E
Methyl Alcohol	G	E	G
Octyl Alcohol	G	G	G
Propyl Alcohol	G	G	G
Triethanolamine	E	E	E
ORGANIC ACIDS			
Acetic Acid	G	E	G
Carbolic Acid (Phenol)	E	G	G
Citric Acid	E	E	E
Formic Acid	P	G	F
Lactic Acid	G	E	E
Malic Acid	G	F	G
Oleic Acid	G	G	G
Stearic Acid (158 F)	G	G	G
Tannic Acid	E	E	E
INORGANIC ACIDS			
Carbonic Acid	G	G	E
Chlorine Water	G	G	G
Hydrobromic Acid	F	G	F
-38% Hydrochloric Acid Conc	F	G	F
48% - 52% Hydrofluoric Acid	G	P	G
Hydrogen Sulfide	G	G	G
Nitric Acid - 10%	G	G	E
Nitric Acid Conc - 70%	G	P	G
Perchloric Acid	F	F	F
Phosphoric Acid Conc - 85%	E	G	G
Sulfuric Acid - 50%	G	E	G
Sulfuric Acid Conc- 93%	P	F	F

SALTS & ALKALIES	CHEMTEx	NEOTEx	PROTEx
Ammonium Hydroxide	E	E	E
Ammonium Sulfate	G	E	G
Calcium Chloride	G	E	E
Calcium Hypochlorite	E	E	E
Potassium Hydroxide	G	E	G
Copper Chloride	E	E	E
Copper Sulfate	E	E	E
Ferric Chloride	E	E	E
Potassium Dichromate	G	E	G
Sodium Hydroxide	E	E	G
ORGANIC ESTERS			
Amyl Acetate	F	E	F
Butyl Acetate	F	E	F
Dibutyl Phthalate	P	F	P
Ethyl Acetate	F	G	F
Ethyl formate	F	E	G
Methyl Acetate	F	G	G
Propyl Acetate	F	G	F
Tricresyl Phosphate	F	F	F
Zinc Acetate - 10%	E	E	E
MISCELLANEOUS			
Acrylonitrile	F	G	F
Aniline	G	G	G
Battery Acid	G	E	E
Butter (158 F)	G	G	G
Buttermilk	E	G	G
Carbon Disulfide	F	G	G
Chlorophenol	F	G	F
Chlorobenzene	F	P	F
Chlorox	E	E	E
Cresol	G	G	G
Dichlorobenzene	G	G	G
Dibenzyl Ether	F	G	F
Ethyl Ether	F	G	F
Hydrazine	G	F	G
Hydrogen Peroxide - 30%	E	G	E
Milk	E	E	E
Monoethanolamine	G	F	G
Morpholine	P	G	P
Paint Remover	G	G	G
Soaps	E	E	E
Tetrahydrofuran	P	G	P

Actual applications and conditions may vary from our laboratory testing, and therefore the information contained in the above chart should be used as a guide only. Users are advised to conduct their own evaluations to determine the suitability of the protective clothing for each specific application. ONGUARD INDUSTRIES MAKES NO WARRANTIES REGARDING THE PROTECTION AFFORDED BY PARTICULAR PROTECTIVE CLOTHING AS PRESENTED. ONGUARD OFFERS NO WARRANTIES OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR USE. ONGUARD INDUSTRIES HEREBY DISCLAIMS ALL WARRANTIES EXPRESSED AND IMPLIED.

E.....Excellent G.....Good
F.....Fair P.....Poor